

Athena 2210

Double Sided Copper Foil Tape

Created: 2010-12-28
Updated: 2018-01-04

GENERAL INFORMATION



Athena 2210 is a double sided copper foil tape coated with conductive adhesive on both sides. It provides electrical conductivity through bonded substrates.

- 0,085mm thick
- Conductive synthetic resin adhesive
- Temperature resistant up to 155°C
- Suitable for shielding

Athena 2210 is available in all dimensions but standard widths are:

- 12mm x 33m
- 19mm x 33m
- 25mm x 33m

CONSTRUCTION



- White paper liner
- Conductive synthetic resin adhesive
- Copper foil carrier
- Conductive synthetic resin adhesive
- White paper liner

APPLICATIONS

Athena 2210 is used for a wide range of electrical applications. The tape is good for applications that require electrical conductivity between substrates and through the adhesive and carrier. Typical applications are for example:

- Bonding of conductive surfaces
- EMI/RFI shielding
- Mounting of electrical components
- Electrical grounding

USER GUIDELINES

To obtain optimal adhesion the surfaces must be clean and dry. Most frequent cleaning solvent is isopropyl/water (50:50 mixture) alcohol. Use safety instructions before using cleaners. Sometimes depending on surface a primer can be used to obtain a higher bonding force. Ideal temperature for tape application is between 21°C and 38°C. Usually electronic components and devices do not need to be cleaned as above.

PRODUCT DATA

Physical Data:

Adhesive:	Conductive synthetic resin
Carrier:	Soft copper foil
Thickness:	Carrier: 0,035mm Adhesive: 0,025mm Total: 0,085mm
Liner:	White siliconised paper
Colour:	Copper
Shelf life*:	5 years
Storage:	Good storage conditions are in room temperature. Not recommended for direct exposure to sunlight or ultraviolet light.

* From date of dispatch by ATC Tape Converting AB

Performance Data:

Tensile strength:	40 N/10mm
Adhesive strength:	4,5 N/10mm
Electrical resistance through adhesive**:	0,003 Ohms
Heat resistance:	Up to +155°C

** Tested according to MIL STD 202F Method 307 across surface area of 1 sq.inch

USAGE

All metal foil based tapes have a tendency to be malleable, which may have an impact on the tape's performance. Therefore, it is important to remove any deformations or kinks that may occur when applying the tape. This can be accomplished by smoothly rolling the tape once it has been applied in position. This process will remove all deformations that can arise during manual application of the tape.

CONTACT INFORMATION

ATC Adhesive Tape Converting AB
Veddestavägen 17, Box 575
175 26 Järfälla, SWEDEN

Telephone: +46 (0)8-564 708 80
Fax: +46 (0)8-564 708 89

E-mail: info@atc.se
Web: www.atc.se

